

Urethane R

Hydrophobic
Urethanes

DESCRIPTION

Urethane R is a hydrophobic chemical grouting compound designed to fill in concrete structural gaps such as a big chasm made by faulty substance, cracks, or joints and to stop high-pressure water leaks. When **Urethane R** comes in contact with water, this dark brown transparent non-flammable liquid expands and quickly seals to a **rigid** closed-cell polyurethane foam that is resistant to most organic solvents, mild acids, alkali and resistant to micro-organisms. **Urethane R** will seal and cure depending on the amount **Urethane RAcc** used and the temperature conditions (consult reactivity data).

Hydrophilic
Urethanes

Accessories

Please read the **MSDS** literature, prior of usage of the product. Use this product only in well ventilated area. Eye and skin contact should be avoided.

Urethane Grout
Technologies

PHYSICAL PROPERTIES

Uncured

Urethane R

Solids	100%	ASTM D-1259
Viscosity	120 cps @ 68°F	ASTM D-4889
Flash Point	C.O.C. 365 °F	ASTM D-93
Specific Gravity	1.114 (9.30 lbs/gal)	ASTM D-4659 Test B
Color	Black-Brown	

Urethane RAcc

Viscosity	15 cps @ 68° F	ASTM D-4889
Flash Point	C.O.C. 320 ° F	ASTM D-93
Appearance	Clear Liquid	

Cured

Tensile Strength	386.1 KPa (56 psi)	ASTM D-3574 Test E
Density	1,074 Kg/m3 (8.96 lbs/gal)	ASTM D-3574 Test A
Bending Strength	213 psi	
Bond Strength	99 psi	
	255 psi (shearing)	
Shrinkage	0%	
Toxicity	Non-Toxic	

Soil Stabilization

Waterproofing

E-Grout.com

STORAGE

Store in dry areas using original container. Keep away from water and humidity. Maintain spouts closed.

PROCURABLE

Urethane R comes in a 5 gallon container.

Urethane RAcc comes in a 32 oz container.

Urethane grouts are packaged under dry nitrogen to keep moisture out , for extended shelf life.

Reactivity Data

Urethane R

Temperature	% RAcc	Cream Time	Gel Time
50° F	1		19'00"
	3		7'40"
	5		4'30"
68° F	1		9'50"
	3		4'05"
	5		2'24"
86° F	1		6'00"
	3		2'25"
	5		1'33"

PRODUCT WARRANTY

The recommendations and suggestions given in this report are made without any representation or warranty, as they are represented for your own investigation and verification. Products discussed are sold without warranty, expressed or implied, in law or fact and upon the condition that purchasers make their own tests to determine the suitability of such products for their particular purposes. Manufacturer's sole responsibility shall be to replace that portion of the product of this manufacturer which proves to be defective. Manufacturers will not be liable to the buyer or any third person for any injury, loss or damage directly or indirectly resulting from use of or inability to use the product. Users should consider this data only as a supplement to other information gathered by them and must make independent determinations of suitability and completeness of information from all sources to assure proper use and disposal of these materials and the safety and health of employees and customers.

Hydrophobic
Urethanes

Hydrophilic
Urethanes

Accessories

Urethane Grout
Technologies

Soil Stabilization

Waterproofing

E-Grout.com

Rev. 041999

Website: <http://www.pycosa.com>
E-mail: pycosa@pycosa.com

P.O.Box 1222
Friendswood, Tx 77549-1222
Tel. 001+(281) 332-7317
Fax 001+(281) 996-1731
USA